

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : B29C 63/34, 70/16, 70/44, 63/18</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/26919 (43) International Publication Date: 25 June 1998 (25.06.98)</p>
<p>(21) International Application Number: PCT/GB97/03453 (22) International Filing Date: 16 December 1997 (16.12.97) (30) Priority Data: 9626060.9 16 December 1996 (16.12.96) GB (71) Applicants (for all designated States except US): SEVERN TRENT WATER LIMITED [GB/GB]; 2297 Coventry Road, Birmingham B26 3PU (GB). ANGLIAN WATER SERVICES LIMITED [GB/GB]; Anglian House, Ambury Road, Huntingdon, Cambridgeshire PE18 6NZ (GB). YORKSHIRE WATER SERVICES LIMITED [GB/GB]; 2 The Embankment, Sovereign Street, Leeds LS1 4BG (GB). EURO-PROJECTS (LTTC) LIMITED [GB/GB]; Pocket Gate of Breakback Road, Woodhouse Eaves, Loughborough, Leicestershire LE12 8RS (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): BOYCE, Gerard, Stephen [GB/GB]; Stoneybrook, Pasture Lane, Ruddington, Nottinghamshire NG11 6AE (GB). (74) Agent: BARKER, BRETTELL & DUNCAN; 138 Hagley Road, Edgbaston, Birmingham B16 9PW (GB).</p>		<p>(81) Designated States: AU, CA, CZ, GB, JP, MX, NO, NZ, PL, TR, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>

(54) Title: THERMOPLASTIC COMPOSITE PRODUCTS AND METHOD OF LINING PIPEWORK

(57) Abstract

A pipe (4) is rehabilitated by means of a tubular liner (5) which is introduced into the pipe in a contracted form, expanded into contact with the pipe wall, and hardened to retain its form. The liner (5) comprises composite material formed by knitting, braiding or weaving tows of intermingled filaments of thermoplastic and reinforcing fibre, the liner being heated during application to the pipe in order to melt the thermoplastic. The composite material may be created as a sleeve. Alternatively, a sheet of the material may be calendered and rolled up into a tubular form, overlapping edge margins of the sheet being bonded together after expansion of the tube into contact with the pipe wall.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

THERMOPLASTIC COMPOSITE PRODUCTS AND METHOD OF LINING PIPEWORK

This invention relates to the manufacture and use of products
5 fabricated from fibre reinforced thermoplastics composite materials. In particular the invention relates to methods of lining pipework and other ducts with such materials, and to the fabrication of duct liners and pipes from such materials.

10 Within the term "duct", where it is used herein, is included pipes, tubes and conduits, whether for conveying fluids (e.g. a sewer) or for other purposes.

A variety of different techniques are currently in use for
15 rehabilitating existing pipe systems by lining the existing pipework rather than removing and replacing it. Lining existing pipework is generally cheaper, and causes less disruption, than complete replacement programs and is thus widely used in the water and gas supply industries.

20 For instance, the majority of water mains in the UK are cast iron (most having a diameter of 150mm or less). Failure of such pipework due to corrosion (both internal and external) is becoming an increasing problem as existing systems age. It is, for example, estimated that over 50% of all water mains in the UK have been in service for more than
25 forty years and that 20% have been in service for more than eighty years. There is therefore an increasing demand for the development of effective rehabilitation techniques.

Conventional methods for lining pipework include cement and
30 epoxy resin spray coating processes, and "slip lining" processes. The

latter involves inserting a pipe liner, typically fabricated from polyethylene or PVC, into the existing pipework.

Slip lining is carried out in a variety of ways using a variety of different forms of pipe liner. For instance, one type of slip lining widely used in the gas industry, referred to as "swage lining", involves winching an MDPE pipe liner into an in situ pipe having first pulled the liner through a die to reduce its diameter. Once in position the liner will expand and attempt to revert to its original diameter. Thus, after a period of twelve hours or so the liner will expand into a close fit within the host pipe.

An advantage of swage lining, and indeed other slip lining process, is that the liner can provide structural strength to the host pipe to meet requirements of high supply pressures. However, where such structural liners are used, steps must be taken to reduce the diameter of the liner so that it can be drawn into the pipe if a close fit between the liner and the pipe wall is to be obtained. Winch loads used can be very high which can provide an installation hazard. Furthermore, even with "close fit" slip lining techniques, such as swage lining, the liner may not properly revert to a close fit within the host pipe along its entire length if there are variations in the diameter of the pipe. This can result in gaps being left between the liner and the pipe wall which is undesirable. For instance, if the liner fails, fluid may run between the liner and the pipe wall before escaping and thus the externally observable manifestation of a leak or burst in the lining could be a considerable distance from the actual point of failure, making it difficult to identify the location of the failure.

It is an object of the present invention to provide a new method for lining pipework or other form of duct.

According to a first aspect of the present invention there is provided a method of lining a duct comprising:

- inserting into the duct a liner comprising composite material
- 5 comprising filaments of thermoplastic and filaments of reinforcing fibre;
- heating the liner to melt the thermoplastic filaments;
- applying pressure to the heated liner to press it into contact with the duct; and
- enabling or permitting the liner to cool whilst in contact with the
- 10 duct in order to harden the thermoplastic/reinforcing fibre composite.

A suitable composite material is available from Vetrotex International of 767 quai des Allobroges - BP 929, 73009 Chambéry Cedex, France (a subsidiary to St. Gobain) under the registered trade

15 name TWINTEX. TWINTEX is, for instance, available as wound rovings, or woven fabrics, or tows comprising homogeneously intermingled long filaments of thermoplastics such as polypropylene, polyethylene, polyethyleneterephthlate (PET) and polybutylterephthlate (PBT) with E-glass, the glass fibre content typically being 45 to 75 WT%

20 (20 to 50 vol%). The TWINTEX manufacturing process enables the thermoplastic and glass fibre filaments to be mixed "dry" with a high degree of control over the distribution of the two filamentary fibres.

Consolidation of the TWINTEX "prepreg" material into a rigid

25 composite is achieved by heating the material under pressure to melt the thermoplastic and disperse it amongst the glass fibres. Cooling the material then solidifies the thermoplastic which forms a solid matrix around the reinforcing glass fibres.

The homogeneous distribution of the filaments in the TWINTEX product ensures favourable processing conditions of temperature verses pressure and the resultant consolidated composite material has good mechanical properties. Further details of the TWINTEX product are
5 readily available from the manufacturer.

Before consolidation, the composite material is relatively flexible and thus may be inserted into a duct to be lined whilst in a collapsed configuration and subsequently expanded to contact the duct wall.
10

During the installation process, pressure may be applied to the liner material to consolidate the composite during the heating stage and/or in between the heating stage and the cooling stage and/or during the cooling stage.
15

A variety of different methods may be used to heat the liner, including irradiating the liner with infrared radiation, or heating the liner using hot gas or steam.

It is preferred that in the duct lining method according to the present invention a liner comprising glass reinforcing fibres is used (e.g. TWINTEX), and infrared radiation is used to heat the liner. It has been found that glass fibres are particularly responsive/absorbent to shortwave infrared radiation (i.e. wavelength less than $2\mu\text{m}$) in particular frequency
20 ranges. The glass fibres thus heat up relatively quickly and melt the thermoplastic filaments intermingled therewith, with relatively little heat loss to the surroundings. This is particularly advantageous when the method is used to line thermally conductive pipes such as cast iron water
25 mains.

30

As a further means of limiting heat loss from the liner to the duct and surroundings, the liner can be provided with an external layer of insulating plastics material, for instance a thermoplastics material such as is used in the composite.

5

The liner may similarly be provided with an internal layer of plastics material, such as polypropylene or polyethylene, which provides the liner with an internal surface meeting accepted standards for transmission of, for example, potable water supplies.

10

Duct lining methods in accordance with the present invention are not limited to lining in-situ, but could be applied to the lining of new pipes at the place of manufacture. Similarly, methods according to the present invention are not restricted to the provision of internal pipe linings, but may be adapted to provide external pipe covers.

15

In another of its aspects the invention provides a method of applying a lining or cover, respectively, to an interior or exterior surface of a duct comprising:

20

applying a liner/cover to the duct which comprises composite material comprising filaments of thermoplastic and filaments of reinforcing fibre;

heating the composite material to melt the thermoplastic filaments;

applying pressure to the liner/cover to press it into contact with the

25

interior/exterior surface of the duct; and

enabling or permitting the liner/cover to cool whilst in contact with the duct in order to harden the thermoplastic/reinforcing fibre composite.

Moreover, the present invention is not limited to the provision of pipe liners and the lining of pipes. In another of its aspects the invention

30

provides a method of manufacturing a product, comprising knitting, braiding or weaving a composite material from intermingled filaments of thermoplastic and reinforcing fibre (e.g. TWINTEX).

5 The use in such a method of tows of intermingled filaments (e.g. TWINTEX) enables the production of products having a wide variety of configurations, tubular or otherwise. For instance, by knitting to an appropriate pattern a wide variety of pipe fittings and other products could readily be manufactured.

10

Existing industrial knitting machines can be adapted to knit such materials in accordance with the present invention. Varying knitted fabric diameters to suit existing underground pipes having a variety of stretch and recovery properties have been produced using a variety of tuck and
15 other stitch structures. This coupled to circular machine cylinder diameter changes and alternative gauges, give the corresponding preformed wall thickness and stretch and strength characteristics required to contend with pipe applications used in the water industry.

20 In addition various positive feed methods incorporating 'positive feeds tapes' and "storage feeder" methods have been used to provide a 'snag' free continuous prefabricated tube of even quality.

Machine productivity has been improved by identifying a
25 commercial match between gauge, diameter, speed, latch needle head and butt size, take down tension and positive yarn feed. Various yarn lubricants and methods have been incorporated improving yarn take off and runability. The yarn feeder position and design relative to positioning the yarn into the latch needle head has been investigated and set to aid

runability of the "Twintex" yarn drawn from the package, both externally and internally.

Both electrical and mechanical patterning systems were used to
5 identify the most simple yet versatile knitting structure design.

In addition, the use of infrared radiation to heat a thermoplastic/fibre reinforced composite material, and particularly use of infrared radiation of a wave length to which the fibre reinforcement is particularly sensitive, provides advantages in the moulding of products
10 using conventional woven, or similar fibre reinforced thermoplastic composite materials. Thus, according to a further aspect of the present invention there is provided a method of manufacturing a product from a composite material comprising filaments of thermoplastic and filaments of reinforcing fibre, the method comprising;

irradiating the material with infrared radiation to melt the thermoplastic;

consolidating the thermoplastic and reinforcing fibres; and

allowing the thermoplastic to harden with the material in a desired
20 form.

Preferably the reinforcing fibres are glass fibres.

Specific embodiments of the present invention will now be described, by way of example only, with reference to the accompanying
25 drawings, in which:

Figures 1a and 1b are schematic cross sections of two forms of thermoplastic/glass fibre composite tow suitable for use in the present invention.

Figure 2 is a schematic illustration of a pipe lining method in accordance with the present invention;

5 Figure 3 is a schematic illustration of a pipe lining method in accordance with a first preferred embodiment of the present invention;

10 Figure 4 is a schematic illustration of a pipe lining method in accordance with a second preferred embodiment of the present invention;

Figure 5 is a schematic cross section through a pipe liner in accordance with the present invention;

15 Figure 6 is a schematic cross section through an alternative pipe liner in accordance with the present invention; and

20 Figure 7 is a schematic illustration of the manner in which a ferrule can be connected to a pipe lined in accordance with the present invention.

It will be appreciated from the above that all aspects of the present invention involve the use of material comprising filaments of a thermoplastic material and filaments of reinforcing fibres. In particular, 25 the preferred material for use in the present invention is one knitted, braided or woven (or otherwise matted together) from tows comprising substantially continuous filaments of a thermoplastic and similarly continuous reinforcing fibres. More particularly, the preferred material is that available from Vetrotex International under the registered trade name 30 TWINTEX.

Figs. 1a and 1b are cross-sections through two preferred forms of TWINTEX tows for use in the present invention. In both Figs. 1a and 1b the thermoplastic filaments are shown as solid dots 1 whereas the glass reinforcing fibres are shown as circles. The two tows differ from one another in that with the tow of Fig. 1b the intermingled filaments are collectively sheathed by an enveloping layer 3 of thermoplastic (which will generally be the same thermoplastic as that used for the filaments 1).

Referring now to Fig. 2, this is a general schematic of a pipe lining process in accordance with the present invention. An underground host pipe 4 is lined with a pipe liner 5 comprising a hose (i.e. a sleeve) knitted, braided or weaved from TWINTEX tows (generally the hose will be knitted from wound rovings of TWINTEX tows). The liner 5 is drawn into the pipe in a folded contracted configuration (a folded part of the liner being illustrated by reference 5a) using a winch (not shown). Once in position within the host pipe 4, the liner 5 is opened out and pressed into contact with the pipe wall. Heat and pressure is then applied to the liner to melt the thermoplastic filaments (for instance the liner would be heated to a temperature of about 148°C where the thermoplastic is polyethylene) and to compress the liner 5 against the wall 4 of the pipe to consolidate the composite material. The liner 5 is then allowed to cool whilst in contact with the pipe wall, whereupon the thermoplastic hardens, forming a substantially rigid fibre reinforced composite lining.

25

Referring now to Fig. 3, this illustrates use of a robotic pig 6 in the lining process described in relation to Fig. 2. The robotic pig 6 comprises positioning rollers 7 extending from its front end, heating means 8 located behind the positioning rollers 7, and cooling and consolidation rollers 9 extending from its rear end. In use, once the liner

30

5 has been inserted into the host pipe 4 in its folded configuration the pig 6 is passed along the pipe through the liner 5. As the pig 6 progresses through the liner 5 the positioning rollers 7 first open up the folded liner 5a ahead of the pig 6 and position the liner 5 against the wall of the pipe 4. Slight air pressure will inflate the Twintex preform against the surface of the pipe. Immediately behind the positioning rollers, the heating means (which may be for instance a radiative heater, or a hot gas heater) then heat up the liner 5 to a temperature sufficient to melt the thermoplastic. As the pig progresses further, the cooling and consolidation rollers 9 come into contact with the heated area of liner 5 and compress the liner 5 against the surface of the pipe 4 to both consolidate the composite material and to aid cooling of the material to speed up the hardening process. Thus, as the pig 6 travels along the pipe 4 it effectively converts the flexible hose into a fully formed and hardened composite lining.

As mentioned above, the heating means is preferably a shortwave infrared radiator. It has been found that the glass reinforcing fibres are particularly responsive to radiation so that most of the heat energy emitted by the heater is absorbed by the glass fibres and subsequently transmitted to the thermoplastic. This minimises heat loss to the surrounding pipe material and greatly reduces both the energy and time required for heating the lining to the required temperature.

An alternative method of installing the liner 5, whilst still following the general scheme described in relation to Fig. 2, is illustrated by Fig. 4. Here, an inflatable bag 10 (e.g. a bag fabricated from silicone rubber) is inserted into the liner 5. The bag 10 is then inflated with hot gas, both to heat the liner 5 and to compress it against the wall of the pipe 4 to consolidate the thermoplastic and reinforcing fibres. The temperature

and pressure within the bag can be controlled as desired. Subsequently, either the gas within the bag 10 can simply be allowed to cool to allow the thermoplastic to harden, or cold gas can be blown into the bag 10 to replace the hot gas and speed up the cooling process.

5

As a modification to the above method, the gas supplied to the bag 10 could be at ambient temperature and the bag could be heated by other means. For example, electrical heating elements or a system of heated pipes (e.g. carrying hot oil) could be distributed through the wall of the bag 10.

As mentioned above, heat loss to the surrounding pipe and ground can be substantial, greatly increasing the energy and/or time required to heat the liner to the melting point of the thermoplastic. This problem can be particularly significant in the lining of cast iron water mains. Accordingly, the liner may be provided with a covering layer of an insulating plastics material, for instance a thermoplastic the same as that incorporated in the composite material used to fabricate the liner. A cross-section of such a liner is illustrated in Fig. 5. The liner comprises a composite tube 11 provided with an external sheath 12 of polypropylene or similar material.

As a further modification, illustrated in Fig. 6, the inner surface of the liner 11 could also be provided with a layer of plastic material 13, such as polyethylene or polypropylene. This is particularly desirable when a liner is to be used for lining potable water mains. For instance, HDPE is a material widely used for conveying potable water and meets all required standards, which may not necessarily be met by the composite material used in fabricating the liner. Thus, incorporating a layer of HDPE (or similar material) at the inner surface of the liner provides a

barrier between the composite material and the fluid to be conveyed through the liner.

It will be appreciated that the liner may be fabricated with both an
5 external and an internal layer of thermoplastic material such as HDPE.

Because the liner is relative flexible when it is inserted into the host pipe, the insertion process is relatively straightforward. Furthermore, when the liner is expanded and pressed against the surface
10 of the pipe, the flexibility of the liner can readily accommodate variations in the host pipe's diameter.

Knitting of the liner provides a convenient method of speedily manufacturing the liner into any desired shape, length, diameter and wall
15 thickness. Moreover, as mentioned above, using new and existing knitting techniques the liner can be knitted into a variety of configurations. For instance, branches could be knitted into the liner so that a single piece liner can be used to line both a mains pipe and a lateral connection.

20

The liners according to the present invention also have the advantage that separate sections of liner can be readily connected together by simply heating and compressing together ends of respective liner sections together to form a weld. There is thus no need for the use of
25 separate couplings.

In addition, referring to Fig. 7, fitting ferrules to a pipe lined in accordance with the present invention is a relatively straightforward procedure. That is, an inner flange 14a of a ferrule 14 can be readily

fixed and sealed to the pipe liner using a layer 15 of thermoplastic substance or similar.

It will be appreciated that the pipe lining methods discussed above
5 represent only exemplary applications of the present invention. For instance, the above methods can readily be adapted to line or cover pipes at the point of manufacture. For example, modifications of the above methods can be used to provide an internal lining or external covering to a new ductile iron pipe.

10

Moreover, the invention is not limited to the provision of pipes and pipe liners, but the knitting process described herein can be used to produce products of a variety of forms, tubular and otherwise. For instance, a variety of pipe fittings and similar products could readily be
15 prepared by knitting the composite material to an appropriate pre-form.

Furthermore, whilst many aspects of the present invention involve the use of a knitted material, using infrared radiation of a particular wavelength to which the reinforcing fibres are particularly responsive can
20 advantageously be applied to the moulding of any thermoplastic/reinforced fibre composite product, whether or not the composite is knitted, woven or otherwise matted, and whether or not the composite comprises TWINTEx tows or otherwise. The wide applicability of this and other aspects of the present invention will be readily apparent to the
25 appropriately skilled person.

As so far described, the liner introduced into the pipe is relatively flexible, even with thermoplastics coatings applied to the inner and/or outer surfaces of the composite material. Whilst this enables the liner to
30 be collapsed readily, in some circumstances it may be acceptable, or even

- advantageous, for the liner to be stiff and relatively inflexible for introduction into a duct. This can be achieved by at least partially consolidating the composite material (by means of heat and pressure) to create a shaped, self-supporting, pre-form prior to insertion into a duct.
- 5 The pre-form may be in the form of a collapsed tube, the tube being expanded under heat and pressure to line the pipe.

- Alternatively, a sheet of the composite material may be heated and calendered (between opposing cooled rollers) to create consolidated sheet
- 10 material. The stiff sheet material can then be rolled up into a substantially tubular form for insertion as a liner into a pipe, the roll of material being secured by, for example, steel wire. Upon releasing the wire fastenings, with the liner inside the pipe, the roll tends to uncoil to the inside diameter of the pipe. Overlapping edge margins of the pre-
- 15 form can then be bonded together. Suitable joining means for achieving this can include electrical resistance wires which have been incorporated into the sheet of composite material at its margins, or a hot melt adhesive tape. The tape may be heated, by means, for example, of included resistance wires or a metal filler which can be heated by induction. A
- 20 robotic pig may be used to seam weld the joint using, for example, a hot roller, ultrasonics or infra-red, followed by a cold roller.

CLAIMS

1. A method of lining a duct comprising:
inserting into the duct a liner comprising composite material
5 comprising filaments of thermoplastic and filaments of reinforcing fibre;
heating the liner to melt the thermoplastic filaments;
applying pressure to the heated liner to press it into contact with
the duct; and
enabling or permitting the liner to cool whilst in contact with the
10 duct in order to harden the thermoplastic/reinforcing fibre composite.
2. A method according to Claim 1, wherein the liner is inserted into
the duct in a collapsed configuration and is subsequently expanded into
contact with the duct.
- 15 3. A method according to Claim 1 or Claim 2, wherein pressure is
applied to consolidate the liner material as the liner is heated.
4. A method according to any preceding claim, wherein pressure is
20 applied to consolidate the liner material as the liner is cooling.
5. A method according to Claim 5, wherein the composite material of
the liner comprises reinforcing fibres of glass.
- 25 6. A method according to any preceding claim, wherein the liner is
heated by irradiating it with infrared radiation.
7. A method according to any one of Claims 1 to 5, wherein the liner
is heated by means of hot gas or steam.

8. A method according to any preceding claim, wherein subsequent to insertion of the liner into the duct there is passed through the liner apparatus comprising at its front end means for pressing the liner into contact with the pipe wall, heating means positioned to the rear of the pressing means for heating the liner, and consolidating means positioned to the rear of the heating means for applying pressure to the heated liner to consolidate the composite material.
9. A method according to Claim 8, wherein the apparatus further includes cooling means located to the rear of the consolidating means for cooling the consolidated liner.
10. A method according to any one of Claims 1 to 7, wherein subsequent to insertion of the liner into the duct pressurised gas is introduced into the liner to press the liner against the duct, and the gas is heated to heat the liner whilst it is pressed against the duct.
11. A method according to Claim 10, wherein an inflatable bag is inserted into the liner to receive the pressurised gas, the wall of the bag bearing against the liner to press it against the duct.
12. A method according to any preceding claim wherein the liner comprises composite material provided in the form of a sleeve.
13. A method according to any preceding claim wherein the composite material of the liner introduced into the duct is provided as calendered sheet which has been rolled up into a tubular form.
14. A method according to Claim 13 comprising the step of bonding together overlapping margins of the sheet material to form a tube.

15. A method according to any of Claims 12, 13 and 14 in which the composite material is knitted, braided or woven from tows comprising intermingled filaments of thermoplastic and reinforcing fibre.
- 5
16. A method according to Claim 15, wherein the tows comprise from about 40% to about 75% reinforcing fibre by weight.
17. A method according to Claim 15 or Claim 16, wherein the tows
10 comprise between about 20% and about 50% of reinforcing fibre by volume.
18. A method according to any one of Claims 15 to 17, wherein each tow is enveloped in a thermoplastic sheath.
- 15
19. A method according to any one of Claims 15 to 18, wherein filaments of thermoplastic and reinforcing fibres are substantially continuous along the length of each tow.
- 20 20. A method according to any preceding claim, wherein the thermoplastic filaments comprise filaments of a polyolefin or thermoplastic polyester.
21. A method according to any preceding claim, wherein the liner
25 comprises an external layer of a flexible thermoplastics material.
22. A method according to any preceding claim, wherein the liner comprises an internal layer of a thermoplastics material.

23. A method of manufacturing a product, comprising knitting, braiding or weaving a composite material from intermingled filaments of thermoplastic and reinforcing fibre.

5 24. A method according to Claim 23 in which the composite material is in the form of a sleeve.

25. A method according to Claim 23 comprising the steps of calendering the composite material as sheet and rolling up the calendered
10 sheet and securing it in a tubular form.

26. A method according to Claim 25 comprising incorporating into edge margins of the sheet joining means whereby the margins can be bonded together when overlapped to form a tube.

15

27. A method according to any one of Claims 23 to 26, further comprising heating the material to melt the thermoplastic filaments, compressing the material to consolidate the thermoplastic and reinforcing fibres, and cooling the material to harden the product in the desired form.

20

28. A method of manufacturing a product from composite material comprising filaments of thermoplastic and filaments of reinforcing fibre, the method comprising;

25 irradiating the material with infrared radiation to melt the thermoplastic;

consolidating the thermoplastic and reinforcing fibres; and

allowing the thermoplastic to harden with the material in a desired form.

29. A tubular product made by a method according to any one of Claims 23 to 28.
30. A duct liner made by a method according to any one of
5 Claims 23 to 28.
31. A pipe made by a method according to any one of Claims 23 to 28.
32. A method of lining a duct, substantially as hereinbefore described
10 with reference to the accompanying drawings.
33. A method of manufacturing a product from filaments of thermoplastic intermingled with reinforcing fibres substantially as hereinbefore described with reference to the accompanying drawings.
15
34. A duct liner or other tubular product substantially as hereinbefore described with reference to the accompanying drawings.
35. A method of applying a lining or cover, respectively, to an interior
20 or exterior surface of a duct comprising:
applying a liner/cover to the duct which comprises composite material comprising filaments of thermoplastic and filaments of reinforcing fibre;
heating the composite material to melt the thermoplastic filaments;
25 applying pressure to the liner/cover to press it into contact with the interior/exterior surface of the duct; and
enabling or permitting the liner/cover to cool whilst in contact with the duct in order to harden the thermoplastic/reinforcing fibre composite.

1/3




Fig. 1a




Fig. 1b




Fig. 2

2/3




Fig. 3




Fig. 4

3/3




Fig. 5




Fig. 6




Fig. 7

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/03453

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B29C63/34 B29C70/16 B29C70/44 B29C63/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 92 12847 A (PRINCE MFG INC) 6 August 1992 see page 4, line 14 - line 30	23, 24, 27
Y		1-7, 10-22, 29-32, 35
Y	US 5 205 886 A (WHITE) 27 April 1993 see column 1, line 60 - column 4, line 25 see column 5, line 27 - line 49 see figure 1	1-7, 10-22, 29-32, 35
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

20 March 1998

Date of mailing of the international search report

20/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx. 31 651 epo rd,
Fax: (+31-70) 340-3016

Authorized officer

Lanaspeze, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/03453

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>EP 0 630 736 A (BASF CORP) 28 December 1994</p> <p>see column 1, line 6 - line 20 see column 4, line 19 - line 31 see column 5, line 3 - line 10 see column 8, line 40 - line 51 see column 9, line 22 - line 29 see example 2</p>	23,24, 27-29, 33,34
X	<p>EP 0 033 244 A (SMITH H R) 5 August 1981</p> <p>see page 4, line 1 - line 9 see page 5, line 16 - page 6, line 5</p>	23,27, 28,33
X	<p>EP 0 417 827 A (STAMICARBON) 20 March 1991</p> <p>see page 4, line 1 - line 14</p>	23,27,33
A	<p>DE 42 12 448 A (BASF AG) 28 October 1993</p> <p>see claims; figure 2 see column 3, line 7 - line 11</p>	5,6
A	<p>WO 96 18493 A (WOOD JOHN) 20 June 1996</p> <p>see abstract; figures 1-3</p>	8,9
A	<p>EP 0 664 202 A (ASHIMORI IND CO LTD) 26 July 1995</p> <p>see abstract; figures 1-8 see page 5, line 14 - line 30</p>	1
A	<p>GB 2 156 240 A (TOKYO KOGO KABUSHIKI KAISHA) 9 October 1985</p> <p>see abstract; figures</p>	1
A	<p>FR 2 628 507 A (PERES CLAUDINE ;MELEC DIDIER (FR)) 15 September 1989</p> <p>see page 2, line 3 - line 37 see page 4, line 19 - line 27</p>	1

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 97/03453

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9212847 A	06-08-92	US 5176868 A AU 1252392 A CN 1063638 A DE 69218920 D DE 69218920 T EP 0567583 A ES 2102495 T JP 6505208 T MX 9200277 A	05-01-93 27-08-92 19-08-92 15-05-97 17-07-97 03-11-93 01-08-97 16-06-94 01-07-92
US 5205886 A	27-04-93	CA 2041567 A	03-11-91
EP 0630736 A	28-12-94	US 5380477 A CA 2122547 A JP 7042049 A	10-01-95 26-11-94 10-02-95
EP 0033244 A	05-08-81	GB 2067612 A	30-07-81
EP 0417827 A	20-03-91	NL 8902194 A CA 2024218 A JP 3090642 A SU 1833396 A US 5190809 A	18-03-91 01-03-91 16-04-91 07-08-93 02-03-93
DE 4212448 A	28-10-93	NONE	
WO 9618493 A	20-06-96	AU 4266896 A CA 2208166 A EP 0797500 A	03-07-96 20-06-96 01-10-97
EP 0664202 A	26-07-95	JP 6328567 A JP 7251452 A NO 950249 A US 5671778 A CA 2140925 A WO 9427808 A	29-11-94 03-10-95 23-01-95 30-09-97 25-11-94 08-12-94
GB 2156240 A	09-10-85	CA 1222962 A DE 3505107 A FR 2559570 A	16-06-87 22-08-85 16-08-85

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 97/03453

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2156240 A		US 4684556 A	04-08-87
FR 2628507 A	15-09-89	NONE	